

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 07-074011

(43)Date of publication of application : 17.03.1995

(51)Int.Cl.

H01F 1/06
B22F 1/00
B22F 9/04
C22C 38/00

(21)Application number : 05-244020

(71)Applicant : SUMITOMO SPECIAL METALS CO
LTD
SUMITOMO METAL IND LTD

(22)Date of filing : 02.09.1993

(72)Inventor : MAKITA AKIRA
IKEGAMI TAKASHI
HIROZAWA SATORU
KURIYAMA KAZUMASU

(54) MANUFACTURE OF PERMANENT MAGNET POWDER

(57)Abstract:

PURPOSE: To suppress the generation of α -Fe and improve magnetic characteristics by powdering thin stripe extremely quick-cooling alloy into grains which have the average grain diameter in a specific range, nitriding the powder in the N₂ and H₂ mixed gas and resin-bonding the powder as bond magnet.

CONSTITUTION: Melted Nd, Fe and V alloy is extremely quick-cooled by a Cu rotating roll which is 250mm in diameter and 30mm in width. The alloy thin strip is powdered mechanical powdering and powder with the average grain diameter of 200-300 μ m is provided. Then, nitriding is performed in the N₂ and H₂ mixed gas composed of H₂ by 50% mol ratio and N₂ by the rest of the percentage under the reduced pressure of 1atm at the room temperature. The powder is cooled and epoxy resin of 2.0wt.% is mixed. Then, compression molding is performed in the magnetic field of 10kOe with a pressure of 3.0tons/ cm² and resin-curing is performed at 150°C for one hour to manufacture a bonded magnet.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of

rejection]

[Date of requesting appeal against examiner's
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office